

# MIPATEX HDPE TARPAULIN **MT-200**

MIPATEX HDPE Tarpaulins are designed to protect your goods. Waterproof, Rustproof and UV resistant tarpaulin is made of super quality that will last in all climates and environmental conditions.

PROPERTY	METHOD OF TEST	REQUIRED VALUE (AS PER IS 15351:2015)	NOMINAL VALUE*
Breaking Strength before UV Exposure, N min. Warp Weft	IS 1969 (Part 1)	1000 750	1060 810
Elongation at break, % $\pm 5$ Warp & Weft	IS 1969 (Part 1)	20	21
Welded seam strength before UV exposure, N Not less than 65 % of Sr. no.6 (weft)	IS 1969 (Part 1)	488	590
Carbon Black conten, % min	IS 2530: 1963	2.50	2.55
Trapezoid Tear strength, N min.	IS 14293	120	135
Puncture resistance, N min.	Annex D	300	315
Impact Failure load, at 1524 mm drop, gf min. gram force at 50 % failure	Annex E	600	750
Colour fastness to light (for coloured tarpaulins)	IS 2454	No Leakage	No Leakage
Water penetration by static pressure head test before ageing	IS: 7940:1976	No Leakage	No Leakage
Ash Contain, %Max	Annex F	3.00	2.40

\*The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.

The information contained herein is accurate and reliable to the best of our knowledge and provided for reference purposes only.



## MIPA INDUSTRIES

S No. 28/1/5, Kondhwa Road, Near Hotel Garwa Hills, Yewalewadi Pisoli, Pune, Maharashtra, 411048

Phone No. +91-9923126429 / 8605512109

**Toll free : 1800 419 1393**

E-mail : [info@mipaindustries.com](mailto:info@mipaindustries.com) | [www.mipaindustries.com](http://www.mipaindustries.com)

**Order Online at : [www.mipatex.in](http://www.mipatex.in)**

For more information please scan QR code

