

HDPE TARPAULIN

HDPE Tarpaulin Assist Keep Your Assets Covered and Protected

The primary use of HDPE Tarpaulin is covering the material kept outdoor. HDPE tarpaulin has multi-uses like a truck cover, tent, poultry curtains, fumigation cover, waterproof storage, pond liners, emergency makeshift, car-bike cover, and wagon cover. Cover or protect your vehicle, fodder, or wood and building materials at construction sites, keep floors clean using this as a drop sheet when painting or polishing.

HDPE tarpaulin fabrics are manufactured from superior quality raw materials. These woven Laminated fabrics are 100% waterproof, UV Resistant, tear-resistant, durable, flexible, and ensure protection from all weather conditions and durability.

FEATURES:



Light weight




Multi Layered



Tear-Resistant



UV stabilized



100% Waterproof



Flexible yet Tough



100% recyclable



Durable



Colour Options





Raw Materials

Mipa industries always use the best available quality raw products to produce the best quality and world class tarpaulins and other polyethylene products for their valued customers worldwide.

Weather Proof

MIPATEX heavy-duty UV stabilized tarpaulins incorporate high tensile strength and resistance to puncture, cracks and tears. Our products are heavy-duty and generally appropriate for applications that require strength and durability.



Multi-Purpose

Tarpaulins have multi-uses like crop Protection and other humanitarian goods from direct sunshine, rainfall, and wind. Also, it is widely used for temporary shelter in many places like labor shelters, camping, and disaster relief work. The industries use HDPE laminated fabrics to make greenhouse aprons, grow bags, vermi beds, Azolla beds, Vehicle cover and different propose.

Customization

We manufacture a customized tarpaulin with the customer's specific requirements for the proper applications. Different applications require different thicknesses, sizes, and colors of tarpaulin covers, and they will be made according to your needs



WHAT IS THE MAIN USE OF HDPE TARPULIN?

The primary use of HDPE Tarpaulin is covering the material kept outdoor.

- **Wagon cover, Truck cover, Car-Bike cover**
- **Agricultural uses, Ground cover, grain storage cover**
- **Emergency makeshift, Tent**
- **Poultry curtains**
- **Fumigation cover**
- **Industrial equipment cover**
- **Greenhouse aprons**
- **low tunnels**



MT-200 MIPATEX HDPE TARPAULIN

HDPE Tarpaulins are designed to protect your goods. Waterproof, Rustproof and UV resistant tarpaulin is made of super quality that will last in all climates and environmental conditions.



PROPERTY	METHOD OF TEST	NOMINAL VALUE*
Mass g/m ²	Annex B	200
Breaking Strength (N)	IS 1969 (Part 1)	1060 (Warpway) 810 (Weftway)
Elongation at break, % ±5 Warp & Weft	IS 1969 (Part 1)	21
Seam strength UV exposure,	IS 1969 (Part 1)	590
Tear Strength (N)	IS 14293	135
Puncture resistance (N)	Annex D	340
Impact Failure load	Annex E	750
Water penetration	IS: 7940:1976	No Leakage
Ash Contain, %Max	Annex F	2.40

MT-250 MIPATEX HDPE TARPAULIN

HDPE Tarpaulins are designed to protect your goods. Waterproof, Rustproof and UV resistant tarpaulin is made of super quality that will last in all climates and environmental conditions.



PROPERTY	METHOD OF TEST	NOMINAL VALUE*
Mass g/m ²	Annex B	250
Breaking Strength (N)	IS 1969 (Part 1)	1060 (Warpway) 940 (Weftway)
Elongation at break, % ±5 Warp & Weft	IS 1969 (Part 1)	21
Seam strength UV exposure,	IS 1969 (Part 1)	640
Tear Strength (N)	IS 14293	140
Puncture resistance (N)	Annex D	375
Impact Failure load	Annex E	860
Water penetration	IS: 7940:1976	No Leakage
Ash Contain, %Max	Annex F	2.10

MT-300 MIPATEX HDPE TARPAULIN

HDPE Tarpaulins are designed to protect your goods. Waterproof, Rustproof and UV resistant tarpaulin is made of super quality that will last in all climates and environmental conditions.



PROPERTY	METHOD OF TEST	NOMINAL VALUE*
Mass g/m ²	Annex B	300
Breaking Strength (N)	IS 1969 (Part 1)	1350 (Warpway) 1200 (Weftway)
Elongation at break, % ±5 Warp & Weft	IS 1969 (Part 1)	21
Seam strength UV exposure,	IS 1969 (Part 1)	790
Tear Strength (N)	IS 14293	165
Puncture resistance (N)	Annex D	425
Impact Failure load	Annex E	1050
Water penetration	IS: 7940:1976	No Leakage
Ash Contain, %Max	Annex F	2.5

MT-340 MIPATEX HDPE TARPAULIN

HDPE Tarpaulins are designed to protect your goods. Waterproof, Rustproof and UV resistant tarpaulin is made of super quality that will last in all climates and environmental conditions.



PROPERTY	METHOD OF TEST	NOMINAL VALUE*
Mass g/m ²	Annex B	340
Breaking Strength (N)	IS 1969 (Part 1)	1510 (Warpway) 1400 (Weftway)
Elongation at break, % ±5 Warp & Weft	IS 1969 (Part 1)	22
Seam strength UV exposure,	IS 1969 (Part 1)	955
Tear Strength (N)	IS 14293	185
Puncture resistance (N)	Annex D	490
Impact Failure load	Annex E	1150
Water penetration	IS: 7940:1976	No Leakage
Ash Contain, %Max	Annex F	2.30

MIPA INDUSTRIES

S No. 28/1/5, Kondhwa Road,
Near Hotel Garwa Hills, Yewalewadi Pisoli,
Pune, Maharashtra, 411048

Phone No. +91-9923126429 / 8605512109

Toll free : 1800 419 1393

E-mail : info@mipaindustries.com

www.mipaindustries.com

Order Online at : www.mipatex.in



For more information please scan **QR code**

